



SECRET - U.S. OFFICIALS ONLY

- 2 -

25X1

Sinters	5,451	16,076	79,460
Waste from rolling and hammer mills	2,765	8,504	7,000
Blast furnace scrap iron	13,583	6,500	6,500
Martin slag	72,945	46,398	65,000
Sintered slag	4,654	5,644	5,000
Ferro-manganese slag	8,170	1,382	9,000
Pyrite cinder	44,989	43,684	26,500
Blast furnace dust	12,462	18,386	22,000
Total stocks	1,684,570	1,860,960	2,369,087

2. Consumption

	<u>1951</u>	<u>1952</u>	<u>1953</u>
Home iron ores	489,961 tons	569,862 tons	728,297 tons
Krivod Rog ores	1,094,735	1,363,663	1,687,244
<u>Swedish ores</u>			
Type C1	60,891	120,068	295,842
Type C2	162,103	246,532	396,713
Type D	16,890	26,316	5,103
Type A	70,133	81,971	71,254
Type A with Mn	137,721	81,946	57,661
Iron ore from other countries	67,944	124,528	181,092
Scandinavian concentrates	201,929	281,622	364,225
Sinters	121,455	838,623	972,144
Waste from rolling and hammer mills	92,345	112,258	113,553
Cast scrap, spatters, rejects (blow hole)	27,586	25,178	30,532
Blast furnace scrap iron	59,715	41,683	36,959
Martin slag	158,214	162,096	219,431
Sintered slag	28,393	31,624	39,143
Ferro-manganese slag	22,790	26,155	20,318
Pyrite cinder	133,296	142,452	149,310
Blast furnace dust	75,546	104,706	154,980
Refining sinters (spiek zwrotny)	72,850	89,218	114,400
Total consumption	3,084,497	4,470,501	5,638,201

As the figures referring to 1953 are estimated there may be slight changes where actual consumption is concerned. The differences are very small and where a greater amount of one type is used this will be balanced by a corresponding reduction of the amount of another type used.

SECRET - U.S. OFFICIALS ONLY

SECRET - U.S. OFFICIALS ONLY

- 3 -

25X1

3. Standard stocks ordered for 1953

Home iron ores	31,243 tons
Krivoi Rog ores	1,054,527
<u>Swedish ores</u>	
Type C1	184,901
Type C2	247,945
Type D	3,189
Type A	44,533
Type A with Mn	36,038
Ferrous ores from other countries	113,182
Scandinavian concentrates	227,640
Sinters	154,316
Waste from rolling and hammer mills	4,947
Cast scrap, spatters, rejects (blow hole)	7,396
Blast furnace scrap iron	5,441
Martin slag	22,857
Sintered slag	8,307
Ferro-manganese slag	54,770
Blast furnace dust	37,516
 Total	 2,238,748

These figures are covered by home supplies and imports.

25X1

SECRET - U.S. OFFICIAL ONLY